

Phone: 973-509-9456

Fax: 973-509-9460

FiberTech F-50

Water Based, Penetrating Primer, Masonry, Wood, Metal Surface Encapsulant

Description

FiberTech F-50 is a high performance highly flexible, mold resistant, penetrating, stabilizing, water based modified acrylic coating for waterproofing, surface stabilization and protecting all masonry, brick, wood and metal surfaces. It has more than ten times the adhesion of other encasement primers, and will stabilize all previously painted, including lead based painted, and asbestos containing surfaces. Our F-50 is also available with a rust-inhibiting additive (F-50MS) for used on all metal surfaces exhibiting signs of rust. Its unique features are that it's a single component, water-based, ready to use material. Adds weatherization, sound & insulation properties. It is used as a primer in conjunction with our F-51, F-51MR or F-52 Roof Sealer Coats (finish coat). This product is recommended for use, as a primer, on all roofing and masonry surfaces. It is designed to provide a superior first coat seal. It is used in conjunction with our poly mesh scrim fabric, and F-51/F-51MR Sealer coat to provide a waterproof system for damaged or leaking roof surfaces.

Technical Data

Color in container Dry Appearance Volume Solids Flash Point

Theoretical Coverage Recommended Dry Film

VOC

Viscosity For Spray

Shelf Life

Surface Temperature Dry Time @75°F Clean Up Milky White/ blue Clear or blue

45% N/A

90-110 SQ FT/GAL (flat surface)

7-9 dry mils per coat

<25 GMS/LTR 100-105 KU

1 Year+ (Min 45°F Max 100°F)

Min 45°F Max 100°F 2-8 hours @ 75°F

Water

Surface Preparation

Previously painted surfaces should be powerwashed (3,000 psi) prior to application of the F-50. The surface should be clean, free from loose mortar, sand, oils, grease, dirt, chlorides, and loose particulates. Allow new concrete, masonry, and stucco to cure at least 14 days prior to application. All roofing, masonry, brick and mortar surfaces should be allowed to dry prior to application.

Application

Brush, roller or spray.

Roll: Use ¾" to ½" synthetic roller cover. Roll in one direction. Do not over roll.

Conventional Air Spray: Minimum pressure to avoid fingering 2,000 psi. Tips should be .517-.519 Reverse-A-Clean (Heavy Duty, HD, tips are recommended). Fluid Hose ¼" x 100'. Pump should be 795-1595 (Graco) or equivalent.

Warranty

ECI can warrant for a period of up to 20 years from the purchase date of this product that it is free from any manufacturers defects. This limited warranty is in lieu of any other warranty, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for any particular purpose. ECI's sole liability under this limited warranty, shall be at its option, to replace any portion of the product proven to be defective in manufacture. Any defects must be reported to ECI within 30 days from discovery and the limited warranty period. This limited warranty does not extend to abuse of the coatings by owner or building occupants, improper maintenance, water damage, acts of god, or any other causes beyond manufacturers control.